

DERBIGUM® SP FR

The Fire Resistant APP-Bitumen Waterproofing Membrane

Composition of the membrane :

- ▶ DERBIGUM SP FR is composed of a blend made of a specific bitumen modified by noble polymers (high-grade APP also called TPO) & two distinct reinforcements, fiberglass & non-woven polyester.
- ▶ The specificity of the blend & the raw materials chosen ensures its durability & fire resistance.
- ▶ The fiberglass sees to its perfect dimensional stability and heat & UV resistance.
- ▶ The non-woven polyester cares for its resistance to impacts & tearing.



Technical characteristics

	Test method	Expression of result	Values	Units
Flow resistance	EN 1110	MLV	≥ 140	°C
Cold bending	EN 1109	MLV	≤ -15	°C
Tensile strength L/T	EN 12311-1	MDV (±20%)	700/650	N/50 mm
Elongation at break L/T	EN 12311-1	MDV (±15)	45/45	%
Overlap shrink	BDA* test	MLV	0	mm
Dimensional stability	EN 1107-1	MLV	≤ 0.20	%
Tear resistance	EN 12310-1	MLV	≥ 150	N
Resistance to impact	EN 12691(B)	MLV	≥ 1250	mm
Resistance to static load	EN 12730(A)	MLV	≥ 20	kg

MLV : Manufacturer Limited Value / MDV : Manufacturer Determined Value

*BDA = Bureau Dak Advies (NL)

Special characteristics

- Fire resistance In accordance with EN 13501-5, Classification BROOF (t1), (t2), (t3) following method ENV 1187
- Durability **> 30 years** proven by durability studies conducted in different European countries - reports available upon request

Presentation of the product

	Test method	Expression of result	Values	Units
Thickness	EN 1849-1	MDV (±0,2)	3 4 5	mm
Width	EN 1848-1	MLV	1,10 1,10 1,10	m
Length	EN 1848-1	MLV	12,73 7,27 5,46	m
Surface		MLV	14 8 6	m ²
Roll weight		MDV (±2,0)	45 35 32	kg
Number of rolls per pallet			20 25 25	

Storage

Rolls must be carried and stored in a vertical position. The floor must be regular and free of sharped objects.



CERTIFIED B ROOF (t1, t2, t3)
NBN ENV 1187 (test 1, 2, 3)



This document cancels and replaces any other document published previously. In order to improve his products, the manufacturer reserves the right to change them without prior notice.



IMPERBEL sa/nv
Bergensesteenweg 32 - B-1651 Lot
T. +32 (0)2 334 87 00
F. +32 (0)2 377 01 90
E-mail: info@derbigum.com

WWW.DERBIGUM.COM